

Evaluation of water hyacinth extract as an admixture in concrete production.

G.D.O. Okwadha* and D.M. Makomele*

***Department of Civil & Construction Engineering, The Technical University of Kenya**

Abstract

Chemical and mineral admixtures commonly used in the production of self-compacting concrete (SCC) are too expensive and pollute the environment. This study evaluated the effectiveness of using a bio-admixture as partial replacement for Auramix 400 chemical superplasticizer in SCC production. Water hyacinth extract was used for this purpose. Gas Chromatography-Mass Spectrometer analysis revealed concentrations of lingo cellulose, saturated and unsaturated fatty acids which make this admixture a retarder. Water hyacinth extract was added at 0%, 10%, 15%, 20% and 25% replacement of Auramix 400, and the mechanical properties of the concrete were determined. The workability as measured by the slump flow test and T500 were within the recommended values of 500–700 mm and 2–5 s respectively, an indication that the water hyacinth extract can be used as a superplasticizer in a SCC mix. There was an increase in T500 and setting time as superplasticizer replacement was increased. This result indicated that the water hyacinth extract retards the hydration rate and hardening process making the concrete to flow longer hence high flowability and filing ability. The compressive strength increased as the superplasticizer replacement was increased irrespective of the curing period. In addition, water permeability increased with an increase in the amount of water hyacinth extract. The optimum superplasticizer replacement was found to be 20%.

Keywords

Water hyacinth SCCAd mixture Super plasticizer Compressive strength Permeability

Journal of Building Engineering Volume 16, Pages 129-133 (2018)

See more at:

<https://www.sciencedirect.com/science/article/pii/S2352710216303564?via%3Dihub#>